

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 59-168050

(43)Date of publication of application : 21.09.1984

(51)Int.Cl.

C08L 23/06
C08K 5/14

(21)Application number : 58-042969

(71)Applicant : MITSUBOSHI BELTING LTD

(22)Date of filing : 14.03.1983

(72)Inventor : MATSUO TADAO

MATSUOKA FUMIO

YOKOTA NOBUO

YAMAMOTO MASAACKI

(54) ULTRA-HIGH-MOLECULAR-WEIGHT POLYETHYLENE COMPOSITION HAVING IMPROVED RESISTANCE TO FRICTION AND WEAR

(57)Abstract:

PURPOSE: To provide a resin compsn. which gives moldings having improved wear resistance, by blending a specified amount of a ground sinter of an ultra- high-molecular-weight polyethylene and an org. peroxide with said polyethylene powder.

CONSTITUTION: 100pts.wt. ultra-high-molecular-weight polyethylene powder (A) having a viscosity-average MW of at least 1,000,000 and an average MW of at least 3,000,000 (light-scattering method), 20W100pts.wt. ground sinter of said polyethylene (B) (pref. one which has a particle size of 1W10mm, and a relatively low melt viscosity and is not crosslinked with an org. peroxide or the like) obtd. by compression molding said polyethylene, and 0.004W0.2wt% org. peroxide (C) such as dicumyl peroxide are blended together to obtain the desired resin compsn. This resin compsn. gives moldings having a high critical PV value and low wearing rate so that they are suitable for use as sliding parts.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office